


DATASHEET RETROLITE

RTL 50 Y-S HT FR

DESCRIPTION



RETROLITE RTL 50 Y HT FR

HV reflective flame-retardant yellow- silver- yellow tape composed by a fluorescent reflective yellow base on which a silver glass microspheres layer is anchored in the central part of the tape.

The tape has a removable PU support film and a protective liner. It is suitable for application on many different surfaces.

It is UNI EN 20471 certified as per certificate No. **CO 0824200108 - 00 - 00** issued by Centro Tessile Cotoniero e Abbigliamento Spa. It is also certified according to **OEKOTEX STANDARD 100 class I**.

It is a reflective fabric especially designed to:

- ✓ *increase the retro-reflection of the light on garments in low visibility conditions;*
- ✓ *find application on flame retardant garments;*

TECHINICAL SPECIFICATIONS

- ✓ **Removable polyester film:** 140 Micron
- ✓ **Transferable film (microspheres and adhesive):** 150 Micron
- ✓ **PU based heat transfer tape**
- ✓ **Glass Microspheres with constant refractive value:** 1.93
- ✓ **Minimum Refraction:** 330 clx 12'/5"
- ✓ **Weight:** 300 gr/mq
- ✓ **Application settings:** 150°C-160°C per 10-15" according to the main fabric.

COLORIMETRY

Trichromatic coordinates:

Before the exposure → $x = 0,398$ $y = 0,547$ Y $\beta = 1,121$ (luminance factor Beta)
After the exposure → $x = 0,397$ $y = 0,530$ Y $\beta = 0,952$ (luminance factor Beta)

REFRACTION * (Cd/lux m²)

Observation angle	Light angle			
	5°	20°	30°	40°
12'	487.2 – 484.2	513.3 – 508.6	501.8 – 480.9	399.6 – 360.9
20'	319 – 318.3	338 – 331.9	334.7 – 328.1	294.9 – 278.3
1°	47.1 – 46.7	46.1 – 45.8	52.5 – 52.8	46.5 – 40.6
1°30'	15.3 – 15.5	15.3 – 14.9	15.4 – 15.6	20.4 – 22.5

The retro-reflective properties of RETROLITE 50 Y-S HT FR comply with the values required by EN 20471 (class II) as per certificate released by Centro Tessile Cotoniero e Abbigliamento Spa.

PRODUCT SPECIFIC RESISTANCES

RETROLITE RTL 50 Y-S HT FR complies with the values required by:

1. Bending (ISO 7854/A 7500 cycles)
2. Cold bending (ISO 4675 -20°C)
3. Abrasion (UNI 530/2 5000 cycles)
4. ISO 6330 method 2 A - 30 domestic washing cycles at 60°C
5. ISO 14116 – 2015
6. ISO 11612 – 2015
7. ISO 15614 - 2015
8. EN 469 – 2020
9. Photometric Rain Performance Test (EN 471 Annex A)
10. Temperature variations 12 hours at 50°C – 20 hours at -30°C

PRODUCT WASH RESISTANCES

RETROLITE RTL 50 Y-S HT FR complies with the values required by EN 20471 and the following norms in the table:

RTL 50 Y-S HT FR		
NORM	WASHING CYCLES	DESCRIZIONE LAVAGGI
ISO 6330/2A	30	Domestic washing cycles at 60°C
ISO 14116	30	Limited flame spread
ISO 11612	30	Clothing to protect against heat and flame
ISO 15614	30	Wildland firefighting clothing
ISO 469	30	Protective clothing for firefighting activities
AVAILABLE FORMATS		
WIDTH	RUNNING METERS	AVAILABILITY
H 50 mm	100 mt	V
H 75 mm	100 mt	V

Detergent: use only ECE detergent, A type, **without optical brighteners, perborates** or sanitizers such as “Napisan”

- ✓ Optical brighteners, perborates, other brighteners and disinfectants decrease RETROLITE 50 Y-S HT FR performances.
- ✓ Do not use organic solvents, chlorine-based brighteners and strong alkaline substances (pH>8).
- ✓ Do not exceed the temperature of 60°C during the washing process.

DRYING CONDITIONS

- ✓ Air drying is recommended.
- ✓ TUMBLE DRY: do not exceed 80°C.

IRONING

Ironing: do not exceed temperature of 120 °C.

HOW TO USE

- ✓ Common application temperatures: 150°C-160°C per 10-15” at HIGH pressure, according to the main fabric.

CUSTOMIZATION

Special segmentation patterns are available or can be studied according to our customer needs.

FURTHER INFORMATION

- ✓ Before starting the production make sure to run application tests to verify the correct compatibility between the film and the main fabric and to select the best application settings.
- ✓ This film is suitable for the application on many different surfaces (Cotton, Polyester, PVC etc). Waterproof treatments or other specific treatments on the fabric may require special application settings to guarantee this film performances. It is advised to run some application test before starting the production.
- ✓ For fabrics that have very special treatments, it may be necessary to press the fabric twice, making sure that the protective liner has been removed. It may be useful to use a silicone paper with the silicon side facing the film, between the heated plate and the reflective tape.

- ✓ The product must be stocked in a dry environment with a temperature between 15°C and 30°C and far away from heat sources and direct light. The product must be used within one year from the delivery.
- ✓ The product is supplied in 100 running meters reels +/- 0,5mt.

For further information, please contact IRE S.r.l.

SN2510PHA

IRE Srl